

SuperGeo™ Textured LLDPE Nominal Product Specifications

Properties	Test Method	Frequency	Minimum Average Values					
		1	30 mil	40 mil	60 mil	80 mil		
Thickness, mil			Nom. (-10%)	Nom. (-10%)	Nom. (-10%)	Nom. (-10%)		
Lowest individual reading 8 out of 10 Lowest individual reading for any of 10 values	ASTM D5199	Per roll	-15% -20%	-15% -20%	-15% -20%	-15% -20%		
Density, g/cm³ (Maximum)	ASTM D1505	200,000 lb	.939	.939	.939	.939		
Asperity Height ⁽¹⁾	ASTM D7466	Every Roll	16	16	16	16		
Tensile Properties (Each Direction) Strength at Break, lb/in width (N/mm) Elongation at Break, %	ASTM D6693, Type IV	20,000 lb	41 (7) 250	54 (9) 250	81 (14) 250	108 (19) 250		
Tear Resistance, lb (N)	ASTM D1004	45,000 lb	14 (63)	20 (90)	30(135)	40 (178)		
Puncture Resistance, lb (N)	ASTM D4833	45,000 lb	30 (135)	40 (180)	59 (262)	79 (351)		
Carbon Black Content, % (range)	ASTM D1603	20,000 lb	2.0 – 3.0	2.0 – 3.0	2.0-3.0	2.0 – 3.0		
Carbon Black Dispersion	ASTM D5596	45,000 lb	Note (2)	Note (2)	Note (2)	Note (2)		
Standard Roll Dimensions								
Roll Length (2), ft			1.020	790	550			
Roll Length (2), ft			21.5	21.5	21.5			
Roll Area (2), ft			21,930	16,985	11,825			

This data is provided for informational purposes only. Brawler Industries, LLC makes no warranties as to the suitability of the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Brawler Industries, LLC for current updates.





© 2014 Brawler Industries, LLC

MILES CITY, MT 184 Hwy 59 N Miles City, MT . 59301 800.488.3592 406.234.1680 MIDLAND, TX 11701 Co. Rd. 125 W Midland, TX . 79711 800.583.6005 432.563.4005 PLEASANTON, TX 4300 S Hwy 281 Pleasanton, TX . 78064 830.569.4005 HOUSTON, TX 8615 Golden Spike Ln Houston, TX . 77086 800.364.7688 281.272.1660

⁽¹⁾ of 10 readings; 8 of 10 must be \geq 14 mils (53mm), and lowest individual reading must be \geq 12 mils (30mm)

^{(2) 9} of 10 views shall be Category 1 or 2. No more than 1 view from Category 3.

 $^{^{(2)}}Roll$ widths and lengths have a tolerance of $\pm\,1\%$

^{*}Custom material thicknesses also available