

SuperScrim™ D Series

Pro-Forma Data Sheet



Properties	Test Method	Typical Values		
Product		D8	D12	D20
Thickness, Nominal		8	12	20
Weight (lb/1000 ft ²)	ASTM D1505	38	58	74
Grab Tensile Strength (lb)	ASTM D7004	190	220	250
Grab Tensile Elongation (%)	ASTM D7004	30	35	40
Strip Tensile Strength (lb)	ASTM D7003	45	53	60
Strip Tensile Elongation (%)@ scrim break	ASTM D7003	40	40	40
Strip Tensile Elongation (%)@ film break	ASTM D7003	350	670	700
Tongue Tear (lb)	ASTM D5884	15	40	53
CBR Puncture (lb)	ASTM D6241	280	320	336
Bursting Strength (lb/in ²)	ASTM D3786	84	105	136
Water Vapor Transmission (WVT) (g/m ² -day)	ASTM E96	0.40	0.23	0.15
Oxidative Induction Time (OIT)	ASTM D3895			
(a) High Pressure OIT (min.)	ASTM D5885	>1000	>1000	>1000
Roll Dimensions				
Roll Length, ft		8,000'	5500'	4010'
Roll Width, ft		6.167'	6.167'	6.167'
Roll Area, ft ²		49,336	33,918.5'	24,792.67'

This data is provided for informational purposes only. Brawler Industries, LLC makes no warranties as to the suitability of the fitness for a specific use or merchantability of products referred to, no guarantee of satisfactory results upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with Brawler Industries, LLC for current updates.

Typical values listed in this sheet are representative of initial production runs. These values can be revised anytime without notice as additional test data becomes available.



MILES CITY, MT
184 Hwy 59 N
Miles City, MT . 59301
800.488.3592
406.234.1680

MIDLAND, TX
11701 Co. Rd. 125 W
Midland, TX . 79711
800.583.6005
432.563.4005

PLEASANTON, TX
4300 S Hwy 281
Pleasanton, TX . 78064
830.569.4005

HOUSTON, TX
8615 Golden Spike Ln
Houston, TX . 77086
800.364.7688
281.272.1660



© 2015 Brawler Industries, LLC

SE HABLA ESPAÑOL

www.brawler.com